

INDION[®] 220 Na

Description

INDION 220 Na is a high capacity strongly acidic cation exchanger in bead form. It is based on cross linked polystyrene and has a gel structure. The resin contains sulphonic acid functional groups. It is supplied moist in the sodium form.

Applications

INDION 220 Na is used most widely in sodium form for water softening application. It can be used also in two stage de-ionising as the cation exchanger in the hydrogen cycle.

Characteristics	
Appearance	Moist golden yellow beads
Matrix	Styrene divinylbenzene copolymer
Functional Group	Sulphonic acid
Ionic form as supplied	Sodium
Total exchange capacity	1.8 meq/ml, minimum
Moisture holding capacity	50 - 55%
Shipping weight*	790 - 830 kg/m ³
Particle size range	0.3 to 1.2 mm
> 1.2 mm	5.0%, maximum
< 0.3 mm	1.0%, maximum
Uniformity co-efficient	1.7, maximum
Effective size	0.45 to 0.60 mm
Maximum operating temperature	120° C
Operating pH range	0 to 14
Volume change	Na to H, 8% approximately
Resistance to reducing agents	Good
Resistance to oxidizing agents	Generally good, chlorine should be absent
*Weight of resin, as supplied, occupying 1m ³ in a unit after backwashing and draining.	

Packing

HDPE Lined bags	:	25/50 lts
LDPE bags	:	1 cft/25 lts
Super sack	:	1000 lts
Super sack	:	35/40/42 cft
MS/HDPE drums with liner bags	:	180/200 lts
Fiber drums with liner bags	:	7 cft

Storage

Ion exchange resins require proper care at all times. The resin must never be allowed to become dry.

Regularly open the plastic bags and check the condition of the resin when in storage. If not moist, add enough clean demineralised water and keep it in completely moist condition. Always keep the resin drum in the shade. Recommended storage temperature is between 20°C and 40°C.

Safety

Acid and alkali solutions used for regeneration are corrosive and should be handled in a manner that will prevent eye and skin contact. If any oxidising agents are used, necessary safety precautions should be observed to avoid accidents and damage to the resin.

INDION range of Ion Exchange resins are produced in a state-of-the-art ISO 9001 and ISO 14001 certified manufacturing facilities at Ankleshwar, in the state of Gujarat in India.

To the best of our knowledge the information contained in this publication is accurate. Ion Exchange (India) Ltd. maintains a policy of continuous development and reserves the right to amend the information given herein without notice.

INDION[®] is the registered trademark of Ion Exchange (India) Ltd.



ION EXCHANGE (INDIA) LTD.

Corporate Office

Ion House, Dr. E. Moses Road, Mahalaxmi,
Mumbai - 400011 | Tel: +91 22 6231 2000
E-mail: ieil@ionexchange.co.in

Regional and Branch Offices

Bengaluru | Bhubaneswar | Chandigarh | Chennai
Delhi | Hyderabad | Kolkata | Lucknow | Vadodara
Vashi | Visakhapatnam

International Division

R-14, T.T.C MIDC, Thane - Belapur Road, Rabale,
Navi Mumbai - 400 701 | Tel: +91 22 6857 2400
E-mail: export.sales@ionexchange.co.in

Overseas Offices

Bangladesh | Canada | Indonesia | Kenya
Malaysia | Oman | Portugal | Saudi Arabia | Singapore
South Africa | Sri Lanka | Tanzania | Thailand | UAE | USA

Manufacturing Units

India - Ankleshwar | Hosur | Patancheru | Rabale | Verna | Wada

Overseas - Bangladesh | Indonesia | Saudi Arabia | UAE

All India Service and Dealer Network

www.ionexchangeglobal.com | www.ionresins.com

