

# INDION® 930 A

## Description

INDION 930 A is a macroporous grade polyacrylic strong base type I anion exchanger having quaternary ammonium functional groups. The proper mix of loosely bound crosslinks and highly porous matrix provide it better adsorption kinetics for long chain organic molecules. Such type of molecules generally cause fouling of functional polymers.

However INDION 930 A does not face this problem because it is reversible in regeneration cycle. INDION 930 A is osmotically stable and is supplied in chloride form

## Applications

As INDION 930 A resin has better affinity for colouring matters in chloride form. It can be effectively used as a decolouriser in processing of sugars, starch hydrolysates, textile processing waste water etc.

Characteristics	
Appearance	Spherical beads
Matrix	Macroporous polyacrylic crosslinked with divinyl benzene
Functional Group	Quaternary ammonium
Ionic form as supplied	Chloride
Total exchange capacity	0.8 meq/ml, minimum
Moisture holding capacity	65 - 72%
Shipping weight*	670 - 730 kg/m <sup>3</sup>
Particle size range	0.3 to 1.2 mm
> 1.2 mm	5.0%, maximum
< 0.355 mm	2.0%, maximum
Uniformity co-efficient	1.7, maximum
Effective size	0.45 to 0.60 mm
Maximum operating temperature	80° C
Operating pH range	1 to 10 for organic removal
Resistance to reducing agents	Good
Resistance to oxidizing agents	Generally good, chlorine should be absent
*Weight of resin, as supplied, occupying 1m <sup>3</sup> in a unit after backwashing and draining.	

## Packing

HDPE Lined bags	:	25/50 lts
LDPE bags	:	1 cft/25 lts
Super sack	:	1000 lts
Super sack	:	35/40/42 cft
MS/HDPE drums with liner bags	:	180/200 lts
Fiber drums with liner bags	:	7 cft

## Storage

Ion exchange resins require proper care at all times. The resin must never be allowed to become dry.

Regularly open the plastic bags and check the condition of the resin when in storage. If not moist, add enough clean demineralised water and keep it in completely moist condition. Always keep the resin drum in the shade. Recommended storage temperature is between 20°C and 40°C.

## Safety

Acid and alkali solutions used for regeneration are corrosive and should be handled in a manner that will prevent eye and skin contact. If any oxidising agents are used, necessary safety precautions should be observed to avoid accidents and damage to the resin.

INDION range of Ion Exchange resins are produced in a state-of-the-art ISO 9001 and ISO 14001 certified manufacturing facilities at Ankleshwar, in the state of Gujarat in India.

To the best of our knowledge the information contained in this publication is accurate. Ion Exchange (India) Ltd. maintains a policy of continuous development and reserves the right to amend the information given herein without notice.

**INDION**<sup>®</sup> is the registered trademark of Ion Exchange (India) Ltd.



## ION EXCHANGE (INDIA) LTD.

### Corporate Office

Ion House, Dr. E. Moses Road, Mahalaxmi,  
Mumbai - 400011 | Tel: +91 22 6231 2000  
E-mail: ieil@ionexchange.co.in

### Regional and Branch Offices

Bengaluru | Bhubaneswar | Chandigarh | Chennai  
Delhi | Hyderabad | Kolkata | Lucknow | Vadodara  
Vashi | Visakhapatnam

### International Division

R-14, T.T.C MIDC, Thane - Belapur Road, Rabale,  
Navi Mumbai - 400 701 | Tel: +91 22 6857 2400  
E-mail: export.sales@ionexchange.co.in

### Overseas Offices

Bangladesh | Canada | Indonesia | Kenya  
Malaysia | Oman | Portugal | Saudi Arabia | Singapore  
South Africa | Sri Lanka | Tanzania | Thailand | UAE | USA

### Manufacturing Units

India - Ankleshwar | Hosur | Patancheru | Rabale | Verna | Wada

Overseas - Bangladesh | Indonesia | Saudi Arabia | UAE

All India Service and Dealer Network

[www.ionexchangeglobal.com](http://www.ionexchangeglobal.com) | [www.ionresins.com](http://www.ionresins.com)

