

# INDION® CAM 1400

# Description

INDION CAM 1400 is a uniform particle size nuclear grade mixed ion exchange resin. It is a mixture of highly purified and super-regenerated INDION 2230  $\mbox{H}^{+}$  and INDIONGS3000NG in the volume ratio of 1:4.

## **Applications**

INDION CAM 1400 is recommended in any non regenerable mixed bed application where reliable production of the highest quality water is required and where "as supplied" resin must have an absolute minimum of ionic and nonionic contamination.

Characteristics		
Physical		
Appearance	Spherical beads	
Shipping weight*	670 - 710 kg/m³	
Particle size		
< 0.42 mm	1.0%, maximum	
Uniformity co-efficient	1.2, maximum	
Effective size	0.5 to 0.65 mm	
Microscopic examination	Surface cracks not more than 5%	
Chemical	Cation resin	Anion resin
Matrix	Styrene DVB copolymer	Styrene DVB copolymer
Туре	Gel	Gel
Functional group	Sulphonic acid	Quaternary ammonium
Total exchange capacity	1.9 meq/ml	1.1 meg/ml
lonic conversion	99% minimum in H <sup>+</sup> form	94% minimum in OH form 1% maximum in CI form 5% miximum in CO₃ form
Moisture holding capacity	49-55%	48-58%
Beads strength	500g/bead, (avg)	250g/bead, (avg)
Thermal stability	Up to 120° C	Up to 60° C
Chemical stability	Stable in pH range 0-14 Resistant to oxidizing and reducing agents Stable in Radiation field upto 10 <sup>7</sup> rad	

Ionic Impurities		
Iron	20 mg/l, maximum as Fe	
Copper	10 mg/l, maximum as Cu	
Heavy metals	10 mg/l, maximum as Pb	
Water soluble organics	0.1 mg KMnO₄/ml, maximum	
*Weight of resin, as supplied, occupying 1 m³ in a unit after backwashing and draining.		

### **Packing**

HDPE Lined bags (Double Bag Packing): 25/50 Its

LDPE Valve Type bags/ Nylon Vaccum Bags: 1 cft/25 Its

HDPE carboy with liner bags : 25/50 lts

HDPE drums with liner bags : 180 lts

# Storage

Ion exchange resins require proper care at all times. The resins must never be allowed to become dry. The drums should therefore be always kept in shade.

Since INDION CAM 1400 is supplied in highly regenerated condition, any exposure to atmospheric air must be avoided as this will convert it to the carbonate form. The resin drums should therefore be kept in tightly closed condition.

### Safety

Acid and alkali solutions used for regeneration are corrosive and should be handled in a manner that will prevent eye and skin contact. If any oxidising agents are used, necessary safety precautions should be observed to avoid accidents and damage to the resin.

INDION range of lon Exchange resins are produced in a state-of-the-art ISO 9001 and ISO 14001 certified manufacturing facilities at Ankleshwar, in the state of Gujarat in India.

To the best of our knowledge the information contained in this publication is accurate. Ion Exchange (India) Ltd. maintains a policy of continuous development and reserves the right to amend the information given herein without notice.

\*\* is the registered trademark of Ion Exchange (India) Ltd.



### Corporate Office

Ion House, Dr. E. Moses Road, Mahalaxmi, Mumbai - 400011 | Tel: +91 22 6231 2000 E-mail: ieil@ionexchange.co.in

### Regional and Branch Offices

Bengaluru | Bhubaneswar | Chandigarh | Chennai Delhi | Hyderabad | Kolkata | Lucknow | Vadodara Vashi | Visakhapatnam

### International Division

R-14, T.T.C MIDC, Thane - Belapur Road, Rabale, Navi Mumbai - 400 701 | Tel: +91 22 6857 2400 E-mail: export.sales@ionexchange.co.in

#### Overseas Offices

Bangladesh | Canada | Indonesia | Kenya Malaysia | Oman | Portugal | Saudi Arabia | Singapore South Africa | Sri Lanka | Tanzania | Thailand | UAE | USA

Manufacturing Units

India - Ankleshwar | Hosur | Patancheru | Rabale | Verna | Wada

Overseas - Bangladesh | Indonesia | Saudi Arabia | UAE

All India Service and Dealer Network

