

# INDION® CAM 19

## Description

INDION CAM 19 is a nuclear grade mixed ion exchange resin. It is a mixture of highly purified and super regenerated nuclear grade strong acid cation resin. INDION 223 Li and nuclear grade strong base Type I anion resin INDION GS300NG in 1:9 volume ratio.

## Applications

INDION CAM 19 is recommended in any non regenerable mixed bed application where reliable production of the highest quality water is required and where "as supplied" resin must have an absolute minimum of ionic and nonionic contamination.

Characteristics		
<b>Physical</b>		
Appearance	Spherical beads	
Shipping weight*	650 - 690 kg/m <sup>3</sup>	
Particle size range	0.3 to 1.2 mm	
> 1.2 mm	5.0%, maximum	
< 0.3 mm	0.5%, maximum	
Uniformity co-efficient	1.7, maximum	
Effective size	0.45 to 0.60 mm	
Microscopic examination	Surface cracks not more than 5%	
<b>Chemical</b>	<b>Cation resin</b>	<b>Anion resin</b>
Matrix	Styrene DVB copolymer	Styrene DVB copolymer
Type	Gel	Gel
Functional group	Sulphonic acid	Quaternary ammonium
Total exchange capacity	1.9 meq/ml	1.1 meg/ml
Ionic conversion	99% minimum in Li form	94% minimum in OH form 1% maximum in Cl form 5% maximum in CO <sub>3</sub> form
Moisture holding capacity	47-53%	48-58%
Beads strength	500g/bead, (avg)	250g/bead, (avg)
Thermal stability	Up to 120° C	Up to 60° C
Chemical stability	Stable in pH range 0-14 Resistant to oxidizing and reducing agents Stable in Radiation field upto 10 <sup>7</sup> rad	

Ionic Impurities	
Iron	20 mg/l, maximum as Fe
Copper	10 mg/l, maximum as Cu
Heavy metals	10 mg/l, maximum as Pb
Water soluble organics	0.1 mg KMnO <sub>4</sub> /ml, maximum
*Weight of resin, as supplied, occupying 1 m <sup>3</sup> in a unit after backwashing and draining.	

## Packing

- HDPE Lined bags (Double Bag Packing) : 25/50 lts  
 LDPE Valve Type bags / Nylon Vacuum Bags : 1 cft/25 lts  
 HDPE carboy with liner bags : 25/50 lts  
 HDPE drums with liner bags : 180 lts

## Storage

Ion exchange resins require proper care at all times. The resins must never be allowed to become dry. The

drums should therefore be always kept in shade. The resin drums should therefore be kept in tightly closed condition.

## Safety

Acid and alkali solutions used for regeneration are corrosive and should be handled in a manner that will prevent eye and skin contact. If any oxidising agents are used, necessary safety precautions should be observed to avoid accidents and damage to the resin.

INDION range of Ion Exchange resins are produced in a state-of-the-art ISO 9001 and ISO 14001 certified manufacturing facilities at Ankleshwar, in the state of Gujarat in India.

To the best of our knowledge the information contained in this publication is accurate. Ion Exchange (India) Ltd. maintains a policy of continuous development and reserves the right to amend the information given herein without notice.

**INDION**<sup>®</sup> is the registered trademark of Ion Exchange (India) Ltd.



## ION EXCHANGE (INDIA) LTD.

### Corporate Office

Ion House, Dr. E. Moses Road, Mahalaxmi,  
 Mumbai - 400011 | Tel: +91 22 6231 2000  
 E-mail: ieil@ionexchange.co.in

### International Division

R-14, T.T.C MIDC, Thane - Belapur Road, Rabale,  
 Navi Mumbai - 400 701 | Tel: +91 22 6857 2400  
 E-mail: export.sales@ionexchange.co.in

### Regional and Branch Offices

Bengaluru | Bhubaneswar | Chandigarh | Chennai  
 Delhi | Hyderabad | Kolkata | Lucknow | Vadodara  
 Vashi | Visakhapatnam

### Overseas Offices

Bangladesh | Canada | Indonesia | Kenya  
 Malaysia | Oman | Portugal | Saudi Arabia | Singapore  
 South Africa | Sri Lanka | Tanzania | Thailand | UAE | USA

### Manufacturing Units

India - Ankleshwar | Hosur | Patancheru | Rabale | Verna | Wada

Overseas - Bangladesh | Indonesia | Saudi Arabia | UAE

All India Service and Dealer Network

[www.ionexchangeglobal.com](http://www.ionexchangeglobal.com) | [www.ionresins.com](http://www.ionresins.com)

