

INDION[®] CAM 1900

Description

INDION CAM 1900 is a nuclear grade controlled particle size mixed ion exchange resin. It is a mixture of highly purified and super regenerated nuclear grade strong acid cation resin. INDION 2230 Li and nuclear grade strong base Type I anion resin INDION GS3000 NG in 1:9 volume ratio.

Applications

INDION CAM 1900 is recommended in any non regenerable mixed bed application where reliable production of the highest quality water is required and where "as supplied" resin must have an absolute minimum of ionic and nonionic contamination.

Characteristics		
Physical		
Appearance	Spherical beads	
Shipping weight*	650 - 690 kg/m ³	
Uniformity co-efficient	1.2, maximum	
Effective size	0.5 to 0.65 mm	
Fines content (< 0.42 mm)	1% maximum	
Microscopic examination	Surface cracks not more than 5%	
Chemical	Cation resin	Anion resin
Matrix	Styrene DVB copolymer	Styrene DVB copolymer
Type	Gel	Gel
Functional group	Sulphonic acid	Quaternary ammonium
Total exchange capacity	1.9 meq/ml	1.1 meq/ml
Ionic conversion	99% minimum in Li form	94% minimum in OH form 1% maximum in Cl form 5% maximum in CO ₃ form
Moisture holding capacity	47-53%	48-58%
Beads strength	500g/bead, (avg)	250g/bead, (avg)
Thermal stability	Up to 120° C	Up to 60° C
Chemical stability	Stable in pH range 0-14 Resistant to oxidizing and reducing agents Stable in Radiation field upto 10 ⁷ rad	

Ionic Impurities	
Iron	20 mg/l, maximum as Fe
Copper	10 mg/l, maximum as Cu
Heavy metals	10 mg/l, maximum as Pb
Water soluble organics	0.1 mg KMnO ₄ /ml, maximum
*Weight of resin, as supplied, occupying 1 m ³ in a unit after backwashing and draining.	

Packing

HDPE Lined bags (Double Bag Packing)	: 25/50 lts
LDPE Valve Type bags / Nylon Vacuum Bags	: 1 cft/25 lts
HDPE carboy with liner bags	: 25/50 lts
HDPE drums with liner bags	: 180 lts

Storage

Ion exchange resins require proper care at all times. The resins must never be allowed to become dry. The

drums should therefore be always kept in shade. The resin drums should therefore be kept in tightly closed condition.

Safety

Acid and alkali solutions used for regeneration are corrosive and should be handled in a manner that will prevent eye and skin contact. If any oxidising agents are used, necessary safety precautions should be observed to avoid accidents and damage to the resin.

INDION range of Ion Exchange resins are produced in a state-of-the-art ISO 9001 and ISO 14001 certified manufacturing facilities at Ankleshwar, in the state of Gujarat in India.

To the best of our knowledge the information contained in this publication is accurate. Ion Exchange (India) Ltd. maintains a policy of continuous development and reserves the right to amend the information given herein without notice.

INDION[®] is the registered trademark of Ion Exchange (India) Ltd.



ION EXCHANGE (INDIA) LTD.

Corporate Office

Ion House, Dr. E. Moses Road, Mahalaxmi,
Mumbai - 400011 | Tel: +91 22 6231 2000
E-mail: ieil@ionexchange.co.in

Regional and Branch Offices

Bengaluru | Bhubaneswar | Chandigarh | Chennai
Delhi | Hyderabad | Kolkata | Lucknow | Vadodara
Vashi | Visakhapatnam

International Division

R-14, T.T.C MIDC, Thane - Belapur Road, Rabale,
Navi Mumbai - 400 701 | Tel: +91 22 6857 2400
E-mail: export.sales@ionexchange.co.in

Overseas Offices

Bangladesh | Canada | Indonesia | Kenya
Malaysia | Oman | Portugal | Saudi Arabia | Singapore
South Africa | Sri Lanka | Tanzania | Thailand | UAE | USA

Manufacturing Units

India - Ankleshwar | Hosur | Patancheru | Rabale | Verna | Wada

Overseas - Bangladesh | Indonesia | Saudi Arabia | UAE

All India Service and Dealer Network

www.ionexchangeglobal.com | www.ionresins.com

