

INDION® 180

Description

INDION 180 resin is a macroporous strongly acidic cation exchanger developed for heterogeneous acid catalytic application.

INDION 180 is supplied in dry form as opaque, grey coloured spherical beads. A proper mix of high cross linking and porosity gives this product outstanding physical stability with high concentration of acid groups.

The unique structure of INDION 180 provides genuine porosity and a strong matrix together, with small volume change in different solutions and solvents. The large surface area leads to high catalytic activity. The functional groups throughout the entire structure are readily accessible to liquid or gaseous reactants thus ensuring efficient performance. The main applications are alkylation, esterification, etherification, condensation, hydrolysis and also for specialised applications such as MTBE.

Characteristics

Appearance	:	Opaque grey to dark grey beads
Matrix	:	Styrene divinylbenzene copolymer
Functional Group	:	Sulphonic acid
Ionic form as supplied	:	Hydrogen
Concentration of acid sites	:	5.0 meq/dry g, minimum
Moisture content	:	1.0 %, maximum
Particle size range	:	0.42 to 1.2 mm
	:	> 1.2 mm : 5.0%, maximum
	:	< 0.42 mm : 5.0%, maximum
Maximum operating temperature	:	130 °C
Operating pH range	:	0 to 7

Reuse of INDION 180

On completion of the catalytic reaction, the resin should be filtered off the products. The solvent as well as unreacted reactants associated with the resin should be washed off by rinsing with either solvent or one of the reactants. These washings can then be reused in subsequent batch processes. If water formation exists in the reaction after filtration, dry the resin. This can be carried out in an oven at about 90°C to 100°C for 6 to 10 hours to reduce moisture content to less than 5%.

Packing

HDPE carboys with inner
double plastic liner bags 25 / 50 kgs

Storage

Ion exchange resin catalysts are hygroscopic in nature. Therefore it is essential to store the dry INDION 180 in tightly packed containers, to prevent absorption of atmospheric moisture. In case moisture has been absorbed, it can be dried at 90°C - 100°C as mentioned above.

Safety

Acid and alkali solutions used for regeneration are corrosive and should be handled in a manner that will prevent eye and skin contact. If any oxidising agents are used, necessary safety precautions should be observed to avoid accidents and damage to the resin.

INDION range of ion exchange resins are produced in state-of-the-art ISO 9001 and ISO 14001 certified manufacturing facility at Ankleshwar, Gujarat.

To the best of our knowledge the information contained in this publication is accurate. Ion Exchange (India) Ltd. maintains a policy of continuous development and reserves the right to amend the information given herein without notice.

INDION is the registered trademark of Ion Exchange (India) Ltd.

ION EXCHANGE (INDIA) LTD.

Corporate Office

Ion House, Dr. E. Moses Road,
Mahalaxmi, Mumbai 400 011
Tel: +91 22 3989 0909 | Fax: +91 22 2493 8737
E-mail: ieil@ionexchange.co.in

International Division

R - 14, T.T.C MIDC, Thane - Belapur Road,
Rabale, Navi Mumbai 400 701
Tel: +91 22 3989 0909 / 3913 2400 | Fax: +91 22 2769 7918
E-mail: export.sales@ionexchange.co.in

OFFICES

Regional	Telephone	Fax	E-mail
Chennai	+91 44 3989 0909 / 3910 2900	+91 44 2815 3361	checro@ionexchange.co.in
Delhi	+91 11 3989 0909 / 3054 3200	+91 11 2577 4837	delcro@ionexchange.co.in
Kolkata	+91 33 3989 0909 / 3043 3400	+91 33 2400 4345	calcro@ionexchange.co.in
Vashi	+91 22 3989 0909 / 3913 2300	+91 22 2788 9839	mumcro@ionexchange.co.in
Branch			
Bengaluru	+91 80 2204 2888	+91 80 2853 2002	bngcro@ionexchange.co.in
Bhubaneswar	+91 674 326 9525 / 257 1491		bbsr@ionexchange.co.in
Chandigarh	+91 172 274 5011	+91 172 274 4594	delcro@ionexchange.co.in
Hyderabad	+91 40 3066 3101 / 02 / 03	+91 40 3066 3104	hydcro@ionexchange.co.in
Lucknow	+91 522 319 9911	+91 11 2577 4837	lko.general@ionexchange.co.in
Vadodara	+91 265 302 7489 / 90	+91 265 2352 932	brdcro@ionexchange.co.in
Visakhapatnam	+91 891 324 6253		sales.vizag@ionexchange.co.in

Factories: Ankleshwar | Hosur | Patancheru | Rabale | Verna

All India Service and Dealer Network

www.ionresins.com