

INDION® 225 H NS

Description

INDION 225 H NS is a non solvent cation exchanger resin that is being produced without the use of environmentally harmful solvents. It is based on cross linked polystyrene strongly acidic cation resin with high capacity and has a dark brown translucent

bead. The resin contains a sulphonic acid functional groups.

INDION 225 H NS is used moist in hydrogen form for coflow and counter flow modes as a first stage in demineralising for the removal of cations. Special grades are available for use in mixed bed units.

Characteristics	
Appearance	Dark brown to black colour beads
Matrix	Styrene Divinylbenzene Copolymer
Functional group	Sulphonic acid
Ionic form as supplied	Hydrogen
Total exchange capacity	1.8 meq/ml, minimum
Moisture holding capacity	49 – 55 %
Shipping weight*	750 – 800 kg/m ³
Particle size range	0.3 to 1.2 mm
> 1.2 mm	5.0 %, minimum
< 0.30 mm	1.0 %, maximum
Effective Size	0.45 to 0.60
Uniformity Coefficient	1.7, maximum
Maximum operating temperature	120 ⁰ C
Operating pH range	0 to 14
Resistance to reducing agents	Good
Resistance to oxidizing agents	Generally good, chlorine should be absent
*Weight of resin, as supplied, occupying 1 m ³ in a unit after backwashing and draining.	

Packing

HDPE Lined bags	:	25/50 lts
LDPE bags	:	1 cft/25 lts
Super sack	:	1000 lts
Super sack	:	35/40/42 cft
MS/HDPE drums with liner bags	:	180/200 lts
Fiber drums with liner bags	:	7 cft

Storage

Ion exchange resins require proper care at all times. The resins must never be allowed to become dry. Repeated drying and rewetting

produce stresses analogous to those due to osmotic shock and can lead to fragmentation of Ion exchangers.

Safety

Acid and alkali solutions used for regeneration are corrosive and should be handled in a manner that will prevent eye and skin contact. If any oxidizing agents are used, necessary safety precautions should be observed to avoid accidents and damage to the resin.

INDION range of Ion Exchange resins are produced in a state-of-the-art ISO 9001 and ISO 14001 certified manufacturing facilities at Ankleshwar, in the state of Gujarat in India.

To the best of our knowledge the information contained in this publication is accurate. Ion Exchange (India) Ltd. maintains a policy of continuous development and reserves the right to amend the information given herein without notice.

INDION[®] is the registered trademark of Ion Exchange (India) Ltd.



ION EXCHANGE (INDIA) LTD.

Corporate Office

Ion House, Dr. E. Moses Road, Mahalaxmi,
Mumbai - 400011 | Tel: +91 22 6231 2000
E-mail: ieil@ionexchange.co.in

International Division

R-14, T.T.C MIDC, Thane - Belapur Road, Rabale,
Navi Mumbai - 400 701 | Tel: +91 22 6857 2400
E-mail: export.sales@ionexchange.co.in

Regional and Branch Offices

Bengaluru | Bhubaneswar | Chandigarh | Chennai
Delhi | Hyderabad | Kolkata | Lucknow | Vadodara
Vashi | Visakhapatnam

Overseas Offices

Bangladesh | Canada | Indonesia | Kenya
Malaysia | Oman | Portugal | Saudi Arabia | Singapore
South Africa | Sri Lanka | Tanzania | Thailand | UAE | USA

Manufacturing Units

India - Ankleshwar | Hosur | Patancheru | Rabale | Verna | Wada | Roha Overseas - Bangladesh | Indonesia | Saudi Arabia | UAE
All India Service and Dealer Network

www.ionexchangeglobal.com | www.ionresins.com

