

INDION® MB 11

Description

INDION MB 11 is a mixed bed ion exchange resin. It is a mixture of highly purified and super regenerated strong acid cation and strong base anion resins in 1: 1 volume ratio.

Applications

INDION MB 11 is recommended in any non regenerable mixed bed application where reliable production of the highest quality water is required and where "as supplied" resin must have an absolute minimum of ionic and nonionic contamination.

Characteristics		
Physical		
Appearance	Spherical beads	
Shipping weight*	710 - 750 kg/m ³	
Particle size range	0.3 to 1.2 mm	
> 1.2 mm	5.0%, maximum	
< 0.3 mm	1.0%, maximum	
Uniformity co-efficient	1.7, maximum	
Effective size	0.45 to 0.65 mm	
Microscopic examination	Surface cracks not more than 5%	
Chemical	Cation resin	Anion resin
Matrix	Crosslinked polystyrene	Crosslinked polystyrene
Type	Gel	Gel
Functional group	Sulphonic acid	Quaternary ammonium
Total exchange capacity	1.9 meq/ml	1.0 meq/ml
Ionic conversion	99% minimum in H form	90% minimum in OH form
Moisture holding capacity	49-55%	48-58% (in Cl form)
Thermal stability	Up to 120° C	Up to 60° C
Chemical stability	Stable in pH range 0-14 Resistant to oxidizing and reducing agents	
*Weight of resin, as supplied, occupying 1 m ³ in a unit after backwashing and draining.		

Variants

INDION MB 11 resin is also available with the additional feature of colour change at exhaustion. Three variants of this colour indicating Indion MB 11 are available:

Indion MB 11 (GVI): Green to Violet

Indion MB 11 (BYI): Blue to Yellow

Indion MB 11 (GOI): Green to Orange

Packing

HDPE Lined bags (Double Bag Packing) : 25/50 lts

LDPE Valve Type bags / Nylon Vacuum Bags: 1 cft/25 lts

HDPE carboy with liner bags : 25/50 lts

HDPE drums with liner bags : 180 lts

Storage

Ion exchange resins require proper care at all times. Resins must never be allowed to become dry. Resins should therefore be always kept in the shade. Since INDION MB 11 is supplied in highly regenerated condition, any exposure to atmospheric air must be avoided as this will convert it to the carbonate form. The resin packing should not be opened during storage.

Safety

Acid and alkali solutions used for regeneration are corrosive and should be handled in a manner that will prevent eye and skin contact. If any oxidising agents are used, necessary safety precautions should be observed to avoid accidents and damage to the resin.

INDION range of Ion Exchange resins are produced in a state-of-the-art ISO 9001 and ISO 14001 certified manufacturing facilities at Ankleshwar, in the state of Gujarat in India.

To the best of our knowledge the information contained in this publication is accurate. Ion Exchange (India) Ltd. maintains a policy of continuous development and reserves the right to amend the information given herein without notice.

INDION[®] is the registered trademark of Ion Exchange (India) Ltd.



ION EXCHANGE (INDIA) LTD.

Corporate Office

Ion House, Dr. E. Moses Road, Mahalaxmi,
Mumbai - 400011 | Tel: +91 22 6231 2000
E-mail: ieil@ionexchange.co.in

Regional and Branch Offices

Bengaluru | Bhubaneswar | Chandigarh | Chennai
Delhi | Hyderabad | Kolkata | Lucknow | Vadodara
Vashi | Visakhapatnam

International Division

R-14, T.T.C MIDC, Thane - Belapur Road, Rabale,
Navi Mumbai - 400 701 | Tel: +91 22 6857 2400
E-mail: export.sales@ionexchange.co.in

Overseas Offices

Bangladesh | Canada | Indonesia | Kenya
Malaysia | Oman | Portugal | Saudi Arabia | Singapore
South Africa | Sri Lanka | Tanzania | Thailand | UAE | USA

Manufacturing Units

India - Ankleshwar | Hosur | Patancheru | Rabale | Verna | Wada

Overseas - Bangladesh | Indonesia | Saudi Arabia | UAE

All India Service and Dealer Network

www.ionexchangeglobal.com | www.ionresins.com

