

INDION[®] TCR

Description

INDION TCR is a crosslinked macroporous ion exchanger having thio-uronium as functional groups. It has been specifically developed for the selective adsorption of mercury and precious metals. INDION TCR is completely insoluble in water and all common solvents. It is stable in acidic as well as alkaline pH range. INDION TCR has excellent physical stability due to its macroporous structure.

It is unaffected by reducing agents. However, INDION TCR can get decrosslinked in the presence of oxidising agents such as chlorine, peroxides, permanganates etc. It is therefore essential to remove all the oxidants from the process stream, before it comes in contact with INDION TCR.

Applications

INDION TCR is specifically used for removing mercury and precious metals from waste water and other streams.

Characteristics	
Appearance	Opaque off white to brown colour beads
Matrix	Crosslinked polystyrene
Functional Group	Thio - uronium
Ionic form as supplied	Hydrogen
Total exchange capacity	1.4 meq/ml, minimum
Moisture holding capacity	41 - 47%
Shipping weight*	670 - 710 kg/m ³
Particle size range	0.3 to 1.2 mm
> 1.2 mm	5.0%, maximum
< 0.3 mm	1.0%, maximum
Uniformity co-efficient	1.7, maximum
Effective size	0.40 to 0.55 mm
Maximum operating temperature	80° C
Operating pH range	1 to 10
Volume change	H ⁺ to Hg ⁺² , -6% approximately
Resistance to reducing agents	Good
Resistance to oxidizing agents	Generally good, chlorine should be absent
*Weight of resin, as supplied, occupying 1m ³ in a unit after backwashing and draining.	

Packing

HDPE Lined bags	:	25/50 lts
LDPE bags	:	1 cft/25 lts
Super sack	:	1000 lts
Super sack	:	35/40/42 cft
MS/HDPE drums with liner bags	:	180/200 lts
Fiber drums with liner bags	:	7 cft

Storage

Ion exchange resins require proper care at all times. The resin must never be allowed to become dry.

Regularly open the plastic bags and check the condition of the resin when in storage. If not moist, add enough clean demineralised water and keep it in completely moist condition. Always keep the resin drum in the shade. Recommended storage temperature is between 20°C and 40° C

Safety

Acid and alkali solutions used for regeneration are corrosive and should be handled in a manner that will prevent eye and skin contact. If any oxidising agents are used, necessary safety precautions should be observed to avoid accidents and damage to the resin.

INDION range of Ion Exchange resins are produced in a state-of-the-art ISO 9001 and ISO 14001 certified manufacturing facilities at Ankleshwar, in the state of Gujarat in India.

To the best of our knowledge the information contained in this publication is accurate. Ion Exchange (India) Ltd. maintains a policy of continuous development and reserves the right to amend the information given herein without notice.

INDION[®] is the registered trademark of Ion Exchange (India) Ltd.



ION EXCHANGE (INDIA) LTD.

Corporate Office

Ion House, Dr. E. Moses Road, Mahalaxmi,
Mumbai - 400011 | Tel: +91 22 6231 2000
E-mail: ieil@ionexchange.co.in

Regional and Branch Offices

Bengaluru | Bhubaneswar | Chandigarh | Chennai
Delhi | Hyderabad | Kolkata | Lucknow | Vadodara
Vashi | Visakhapatnam

International Division

R-14, T.T.C MIDC, Thane - Belapur Road, Rabale,
Navi Mumbai - 400 701 | Tel: +91 22 6857 2400
E-mail: export.sales@ionexchange.co.in

Overseas Offices

Bangladesh | Canada | Indonesia | Kenya
Malaysia | Oman | Portugal | Saudi Arabia | Singapore
South Africa | Sri Lanka | Tanzania | Thailand | UAE | USA

Manufacturing Units

India - Ankleshwar | Hosur | Patancheru | Rabale | Verna | Wada

Overseas - Bangladesh | Indonesia | Saudi Arabia | UAE

All India Service and Dealer Network

www.ionexchangeglobal.com | www.ionresins.com

